POYAD AB270

Anti-Block MB

Description

Product: Anti-Block Master-Batch

• Carrier: Poly Ethylene

· Active ingredients: Inorganic Anti-blocking Agent

Application & Addition Rate

• PE Film: 0.5 to 3% (depends on Film Thickness^(Note) & Requirement)

• PE Sheet: 0.5 to 2% (depends on Sheet Thickness^(Note) & Requirement)

Note: Thinner film/sheet needs more addition rate

Advantages

Avoid Film Blocking During Wind-up

No Significant Effect on Haze & Gloss

Well Dispersed

Typical Properties

Properties		Test method	Value	Unit
Physical	Melt Flow Rate (190 °C/2.16 Kg)	ASTM D 1238	3 ± 1	g/10min
	Density	ASTM D 1505	0.96	g/cm3
	Moisture	ASTM D 644	Max 0.1	%

Food Contact Status

• Food contact approved ref. I.R.I Ministry of Health and Care. For more details please contact us.

Storage & Packaging

- Store in dry place below 30 °C away from sun exposure not to exceed 6 months
- Packed in 20 kg PP raffia bags on 1000 kg stretch-wrapped pallet

NOTICE 2015-03

The information and data contained herein are believed to be correct and given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of product, no warranty is given or is to be implied with respect to such information, nor do we offer any warranty of immunity against infringement.