



## WMB 122C

White MB

### Description

- Product: White Master-Batch
- Carrier: Poly Olefin
- Active Ingredients: Treated Rutile TiO<sub>2</sub>

### Application & Addition Rate

- PE Film: 2 to 10%
- PP Raffia Bag: 2 to 10%
- PE & PP Injection Molded Parts: 1 to 3%
- PE & PP Sheet: 1 to 5%

### Advantages & Features

- Well Dispersed
- Suitable Hiding Power

### Typical Properties

	Properties	Test method	Value	Unit
Physical	Melt Flow Rate (190 °C/5 Kg)	ASTM D 1238	3 ± 1	g/10min
	Active Pigment Content	ASTM D 4218	40 ± 2	
	Density	ASTM D 1505	1.85	g/cm <sup>3</sup>
	Moisture	ASTM D 644	Max 0.2	%

### Food Contact Status

- Food contact approved ref. I.R.I Ministry of Health and Care. For more details please contact us.

### Storage & Packaging

- Store in dry place below 30 °C away from sun exposure not to exceed 12 months
- Packed in 25 kg PP raffia bags on 1250 kg stretch-wrapped pallet

### NOTICE

2015-05

The information and data contained herein are believed to be correct and given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of product, no warranty is given or is to be implied with respect to such information, nor do we offer any warranty of immunity against infringement.