WMB 136 White MB

Description

Product: White Master-Batch

· Carrier: Poly Styrene

Active Ingredients: Treated Rutile TiO2

Application & Addition Rate

PS/ABS Injection Molded Parts: 1 to 3%

• PS Sheet Extrusion: 0.5 to 3

Advantages

Easy Flow and High Processability

Suitable Hiding Power

High Quality RutileTiO2

- Good Compatibility with both PS & ABS
- · Bright White Shade
- Filler Free

Typical Properties

Properties		Test method	Value	Unit
Physical	Melt Flow Rate (200 °C/5 Kg)	ASTM D 1238	20	g/10min
	Active Pigment Content	ASTM D 4218	55± 2	%
	Moisture	ASTM D 644	Max 0.1	%

Food Contact Status

• Food contact approved ref. I.R.I Ministry of Health and Care. For more details please contact us.

Storage & Packaging

- Store in dry place below 30 °C away from sun exposure not to exceed 12 months
- Packed in 25 kg PP raffia bags on 1250 kg stretch-wrapped pallet

NOTICE

2017-09

The information and data contained herein are believed to be correct and given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of product, no warranty is given or is to be implied with respect to such information, nor do we offer any warranty of immunity against infringement.