WMB 122B White MB

Description

Product: White Master-Batch

· Carrier: Poly Olefin

Active Ingredients: Treated Rutile TiO2

Application & Addition Rate

• PE Film: 2 to 10%

• PP Raffia Bag: 2 to 10%

• PE & PP Injection Molded Parts: 1 to 3%

• PE & PP Sheet: 1 to 5%

Advantages

Well Dispersed

Exhibit Bluish Color Shade

Suitable Hiding Power

Typical Properties

	Properties	Test method	Value	Unit
Physical	Melt Flow Rate (190 °C/5 Kg)	ASTM D 1238	3 ± 1	g/10min
	Active Pigment Content	ASTM D 4218	50 ± 2	
	Density	ASTM D 1505	1.85	g/cm3
	Moisture	ASTM D 644	Max 0.2	%

Food Contact Status

• Food contact approved ref. I.R.I Ministry of Health and Care. For more details please contact us.

Storage & Packaging

- Store in dry place below 30 °C away from sun exposure not to exceed 12 months
- Packed in 25 kg PP raffia bags on 1250 kg stretch-wrapped pallet

NOTICE 2015-05

The information and data contained herein are believed to be correct and given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of product, no warranty is given or is to be implied with respect to such information, nor do we offer any warranty of immunity against infringement.